



US 20090302664A1

(19) **United States**(12) **Patent Application Publication**
Galbreath et al.(10) **Pub. No.: US 2009/0302664 A1**(43) **Pub. Date: Dec. 10, 2009**(54) **ENVIRONMENTALLY FRIENDLY LAYERED SEATING ASSEMBLY**(22) Filed: **Aug. 18, 2009****Related U.S. Application Data**(75) Inventors: **Ashford A. Galbreath**, Troy, MI (US); **Asad S. Ali**, Troy, MI (US); **Mark A. Folkert**, Farmington Hills, MI (US); **Scott A. Ziolek**, Ypsilanti, MI (US); **Terry R. O'Bannon**, Royal Oak, MI (US)


(63) Continuation of application No. 11/458,832, filed on Jul. 20, 2006, now Pat. No. 7,585,030.

Publication Classification(51) **Int. Cl.**
A47C 7/18 (2006.01)
B60N 2/44 (2006.01)
B60N 2/58 (2006.01)(52) **U.S. Cl.** **297/452.48**

Correspondence Address:

BROOKS KUSHMAN P.C. / LEAR CORPORATION
1000 TOWN CENTER, TWENTY-SECOND FLOOR
SOUTHFIELD, MI 48075-1238 (US)(57) **ABSTRACT**

The present invention relates to an environmentally friendly layered vehicle seat assembly and a method of making the same. In at least one embodiment, the vehicle seat assembly comprises a cushion composite comprising a structural layer and a cushion layer adjacent to the structural layer, and a trim material secured over the cushion composite.

(73) Assignee: **LEAR CORPORATION**,
Southfield, MI (US)(21) Appl. No.: **12/543,080**




Figure 3

Figure 1




Figure 6




Figure 4




Figure 2




Figure 5

ENVIRONMENTALLY FRIENDLY LAYERED SEATING ASSEMBLY

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a continuation application U.S. patent application Ser. No. 11/458,832 filed Jul. 20, 2006, which is hereby incorporated by reference in its entirety.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The present invention relates to an environmentally friendly layered vehicle seat assembly and a method of making the same.

[0004] 2. Background Art

[0005] Generally speaking, most seat assemblies include three fundamental components: (a) a frame to support the seat assembly and mount it to a body, such as a vehicle; (b) a foam cushion to cover the frame; and (c) trim material to cover foam cushion and provide a durable surface for contact with a seat assembly occupant. Conventional vehicle seating designs typically involve mixing of base construction polymers joined in a manner that is difficult to disassemble and not focused on environmentally friendly material use.

[0006] Accordingly, there is a need to provide a vehicle seat assembly which is environmentally friendly yet structurally sound and comfortable.

SUMMARY OF THE INVENTION

[0007] According to at least one aspect of the present invention, a vehicle seat assembly is provided. In at least one embodiment, the vehicle seat assembly comprises a cushion composite comprising a structural layer and a cushion layer adjacent to the structural layer, and a trim material secured over the cushion composite.

[0008] In at least another embodiment, the vehicle seat assembly comprises a cushion composite comprising an EPP structural layer, a soy-based foam cushion layer adjacent to the structural layer, and a comfort pad adjacent the cushion layer, and a trim material secured over the cushion composite.

[0009] According to at least another aspect of the present invention, a method of making a vehicle seat assembly is provided. In at least one embodiment, the method comprises providing a cushion composite comprising a structural layer and a cushion layer adjacent to the structural layer, and securing a trim material over the cushion composite.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] FIG. 1 is a schematic cut-away environmental view of a vehicle seat assembly in accordance with an embodiment of the present invention;

[0011] FIG. 2 is a schematic sectional view of the vehicle seat assembly illustrated in FIG. 1, taken through line 2-2;

[0012] FIG. 3 is a view similar to FIG. 2 illustrating another embodiment of the present invention;

[0013] FIG. 4 is a view similar to FIG. 3 illustrating another embodiment of the present invention;

[0014] FIG. 5 is a view similar to FIG. 1 illustrating another embodiment of the present invention; and

[0015] FIG. 6 is a schematic side sectional view showing an additional embodiment of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0016] As required, detailed embodiments of the present invention are disclosed herein. However, it is to be understood that the disclosed embodiments are merely exemplary of the invention that may be embodied in various and alternative forms. The figures are not necessarily to scale, some features may be exaggerated or minimized to show details of particular components. Therefore, specific structural and functional details disclosed herein are not to be interpreted as limiting, but merely as a representative basis for the claims and/or a representative basis for teaching one skilled in the art to variously employ the present invention.

[0017] Moreover, except where otherwise expressly indicated, all numerical quantities in the description and in the claims are to be understood as modified by the word "about" in describing the broader scope of this invention. Practice within the numerical limits stated is generally preferred. Also, unless expressly stated to the contrary, the description of a group or class of material as suitable or preferred for a given purpose in connection with the invention implies that mixtures of any two or more members of the group or class may be equally suitable or preferred.

[0018] Referring now to the Figures, where like numerals are used to designate like structures throughout the drawings, a schematic vehicle seat assembly in accordance with at least one embodiment of the present invention is generally shown at 10 in FIG. 1. While the vehicle seat assembly 10 is illustrated in FIG. 1 to be a bucket seat assembly, it should be understood that the principles of the invention are applicable to other types of seat assemblies, such as bench, captain and other types of seat assemblies. It should also be understood that the principles of the present invention are applicable to other configurations where foam is a component such as backrests, back support pads, armrests, and head restraints. Still further, it should also be understood that the principles of this invention are applicable to all types of vehicle seat assemblies as well as non-vehicle seat assemblies.

[0019] As shown in FIG. 1, the vehicle seat assembly 10 includes a seat frame, generally indicated at 14 having a plurality of mounting brackets (not shown) adapted to operatively secure the seat frame within a vehicle. The seat frame 14 may be constructed from any material suitable for application within a vehicle seat assembly 10, such as aluminum, steel or other metal alloy, composite material, or a suitable polymer. Further, the seat frame 14 may be manufactured using techniques commonly known in the art, and relative to the type of material employed. By way of example, manufacturing techniques may include stamping, welding, fastening or molding a suitable material to form the seat frame 14.

[0020] The vehicle seat assembly 10 also includes a seat back, generally indicated at 16, and a lower seat assembly, generally indicated at 18. In at least the illustrated embodiment, the seat back 16 and the lower seat assembly 18 each have the same cushion composite 20 covered by a trim material 22. However, it should be understood that the cushion composite 20 for the seat back 16 can differ from the cushion composite 20 of the lower seat assembly 18. Likewise, it should be understood that the trim material 22 for the seat back 16 can differ from the trim material 22 for the lower seat assembly 18.

[0021] In at least one embodiment, and as shown in FIG. 1, the vehicle seat assembly 10 includes an upper and lower side shields 26 and 28, respectively. The seat shields 26 and 28 can be made of any suitable plastic material such as polypropylene, expanded polypropylene, filler reinforced plastic, or other types of plastic. It should be understood however that one or both of the side shields 26 and 28 could be omitted as desired. Likewise, as will be explained further below, it should be understood that the frame 14 could optionally be omitted as desired. As can best be seen in FIG. 1, the cushion composite 20 is received on or around the frame 14 and the trim material 22 is adapted to engage the cushion composite 20 and/or the frame in a covering relationship.

[0022] As can best be seen in FIGS. 1 and 2, the cushion composite 20 includes a structural layer 30, in at least the illustrated embodiment, disposed over frame 14, and a cushion layer 32 that is disposed over the structural layer 30. The cushion composite 20, as shown in the embodiment illustrated in FIGS. 1 and 2, optionally includes a comfort pad 34 that is disposed over the cushion layer 32. As will be explained further below, each of the layers 30, 32 and 34 cooperate with, and in some embodiments are secured to, each other in a manner such that they are relatively easily separable for recycling at end of use. If any of the layers 30, 32, and 34 are secured to another, suitable securement methods can be used, such as the use of interface fits, surface tension resistance modifications, clips and/or adhesive, in such a manner as to allow for relatively easy separation of the layers.

[0023] The structural layer 30 can be any suitable structural foam material. In at least one embodiment, suitable structural materials will have a rigidity and/or density that is higher than conventional polyurethane foam. In at least one embodiment, suitable structural foam materials have a density of at least 1.75 pounds per cubic foot (pcf), and less than 7.0 pcf. In at least another embodiment, suitable structural foam materials will have a density of 2.0 to 4.0 pcf, and in yet other embodiments of 2.5 to 3.5 pcf. Density of the structural foam material can be measured in accordance with ASTM test method No. D3574.

[0024] In at least one embodiment, suitable structural materials will have a hardness of 150 to 250 N (Newtons), in at least another embodiment of 175 to 230 N, and in at least another embodiment of 190 to 215 N. Hardness can be measured by ASTM test method No. D3574 and at 25% compression or deflection. In at least one embodiment, suitable structural materials will have a compression strength of 20 to 100 psi, in at least another embodiment of 30 to 80, and in at least another embodiment of 35 to 65, as measured in accordance with ASTM test method No. D3574.

[0025] In at least one embodiment, the structural layer 30 comprises a molded expanded polyolefin (EPO) layer. Suitable examples of expanded polyolefin (EPO) include, but are not necessarily limited to, expanded polyethylene (EPE), expanded polypropylene (EPP), expanded polybutylene (EPB), and copolymers of ethylene, propylene, butylene, 1,3-butadiene, and other olefin monomers, such as alpha-olefin monomers having from 5-18 carbon atoms, and/or cycloalkylene monomers such as cyclohexane, cyclopentene, cyclohexadiene, norbornene, and aromatic substituted olefins, such as styrene, alpha-methylstyrene, paramethylstyrene, and the like.

[0026] In at least one particular preferred embodiment, the EPO is expanded polypropylene (EPP) and its copolymers

with ethylene, propylene and butylene. Any suitable EPP may be used, however in at least one embodiment, suitable EPP's include, but are not limited to, ARPRO® EPP available from JSP International and EPP available from SCA Packaging North America.

[0027] Expanded polyolefins can be prepared by a bead polymerization process in which relatively small uniform beads of polymer are produced, containing a gas which is later utilized to effect blowing during the molding process. The most commonly used gas is air although other gases including low boiling point liquids which produce gases at the molding temperatures may be used. Suitable gases include, but are not limited to air, nitrogen, carbon dioxide, pentene and the like.

[0028] While the structural layer 30 can have any suitable size and configuration, in at least one embodiment, the structural layer 30 has an average thickness of 5 to 100 mm, in other embodiments of 20 to 70 mm, and in yet other embodiments of 30 to 50 mm.

[0029] The cushion layer 32 can comprise any suitable cushion material, such as a suitable resilient polymer. In at least one embodiment, suitable cushion materials will have a density of 1.5 to 4.5 pcf, in another embodiment of 2.0 to 3.75 pcf, and in yet other embodiments of 2.7 to 3.0 pcf. Density of the cushion material can be measured by ASTM test method No. D3574. In at least one embodiment, suitable cushion materials will have a hardness of 175 N (Newtons) to 400 N, in other embodiments of 225 to 350 N, and in yet other embodiments of 275 to 325 N. Hardness of the cushion material can be measured by ASTM test method No. D3574. In at least one embodiment, suitable cushion materials will have a hysteresis of 18 to 30 KPa, in another embodiment of 20 to 28 KPa, and in yet other embodiments of 23-26 KPa. Hysteresis of the cushion material can be measured by ASTM test method No. D3574.

[0030] In at least certain embodiments, the cushion material comprises conventional polyurethane foam, soy-based foam, silicone, thermoplastic olefins, thermoplastic urethanes, and/or natural oil-based expanded polyurethanes and the like. In at least one embodiment, because of its environmentally friendly nature, soy-based polyurethane is preferred. Soy-based polyurethane can be made with any suitable soy-based polyols, such as those available, but not necessarily limited to, from Bayer, Urethane Soy Systems, and Dow Chemical. Any suitable soy-based polyurethane may be used, however in at least one embodiment, suitable soy-based polyurethanes include, but are not necessarily limited to those available from Woodbridge Foam and Renosol. The cushion layer 32 can be any suitable size and shape, however, in at least one embodiment, the cushion layer 32 has an average thickness of 20 to 100 mm, and in at least another embodiment of 30 to 70 mm, and in still yet other embodiments of 40 to 60 mm.

[0031] The comfort pad 34 can comprise any suitable comfort layer or pad and can be made of any suitable material that provides good hand feel and soft resilience as the seat assembly 10 is deflected during use. The comfort pad 34 is optionally provided when the cushion layer 32 has a density above 3.0 pcf, as measured according to ASTM test method No. D3574 and/or a hardness above 300 N, as measured according to ASTM test method No. D3574 at a compression of 25%. In at least one embodiment, the comfort pad 34 comprises a sheet of relatively soft material, such as a low hardness foam or a pad of non-woven fibrous materials. While the

comfort pad **34** may have any suitable shape and size and configuration, in at least one embodiment, the comfort pad **34** has an average thickness of 2 to 30 mm, in other embodiments of 5 to 20 mm, and in yet other embodiments of 8 to 15 mm.

[0032] In at least one embodiment, the comfort pad **34** comprises a polyester or nylon non-woven fiber pad. In at least one embodiment, the comfort pad **34** comprises a non-woven compressed fiber material that is compatible, i.e., a similar type of polymer, with the trim material **22**. In at least one embodiment, the comfort pad **34** of non-woven fibrous material comprises a thickness of 5-15 mm and a wt. of 2 to 6 oz.

[0033] In at least another embodiment, the comfort pad **34** comprises a sheet of foam having an average thickness of 8 to 20 mm. In at least one embodiment, the foam comfort pad **34** has a density of 1.8 to 2.5 pcf, as measured according to ASTM test method No. D3574. In at least one embodiment, the foam comfort pad **34** has a hardness of 5 to 12 N, as measured according to ASTM test method No. D3574 at a compression or deflection of 25%. In at least certain embodiments, the foam comfort pad **34** can have an air permeability of above 2.0 cubic feet/minute and/or a compression set (75%) of no more than 20%.

[0034] It should be understood that the structural layer **30**, the cushion layer **32**, and the comfort pad **34** can have any suitable configuration, shape and size. For instance, as shown in FIG. 2, each layer **30**, **32** and **34** have similar sizes and constructions with the structural layer **30** being disposed over the frame **14**, the cushion layer **32** being disposed over the structural layer, and the comfort pad **34** being disposed over the cushion layer.

[0035] As can be seen in FIG. 3, the cushion layer **32** has an inner surface **40** defining a cavity **42** within which the comfort pad **34** is received. Referring to FIG. 3, another embodiment is illustrated. In other words, the structural layer **30** can comprise a generally uniform layer of material disposed on the frame **14** with the cushion layer **32** comprising a hollow layer having a cavity **42** within which the comfort pad **34** is received.

[0036] Referring to FIG. 4, an alternative configuration is shown wherein the structural layer **30** is configured to have a cavity within which the cushion layer **32** is received. As shown in FIG. 4, the comfort pad **34** can extend over both the structural layer **30** and the cushion layer **32** or in another embodiment (not shown) the comfort pad **34** can extend only over the cushion layer **32** or the structural layer **30**. As can be envisioned, may different configurations of the layers **30-34** can be encompassed by the present invention, even those which are not shown or described herein.

[0037] As discussed, the vehicle seat assembly **10** also includes trim material **22** which is adapted to engage the cushion composite **20** in a covering relationship. The trim material **22** may include any material known in the art. By way of example, some of the known materials include cloth, leather or polymers of sufficient quality and thickness for use in seat trim applications. Polymer trim materials may include a flexible close cell polymer skin material such as polyvinyl, polyvinyl chloride (PVC), polyester, nylon, thermoplastic olefin (TPO) or thermoplastic urethane (TPU). Additional materials for use as trim material **22**, may include a foam backing (not shown, but generally known in the art) which may be manufactured from a variety of polymer foam materials. By way of example, the foam backing may be polyethylene, polypropylene, polyurethane, or a polystyrene foam.

Optionally, a mesh or reinforcing material (not shown, but generally known in the art) such as fiberglass, nylon, polyester or natural fibers may be applied to the foam backing or back of the trim material **22** for increase in strength without increasing rigidity. In at least one particularly preferred embodiment, the trim material **22** comprises polyester or nylon trim material having polyester or nylon trim fasteners (not shown) for securing the trim material **22** to one or more components (i.e., cushion **20** and/or frame **14**) of the vehicle seat assembly **10**.

[0038] In at least certain embodiments, the layers **30-34** of the cushion composite **20** are configured so that they can be easily assembled and disassembled to facilitate assembly and end of line disassembly for recycling. In at least one embodiment, the layers **30-34** are not secured to each other by any suitable mechanical fastening. In this embodiment, the layers **30-34** are either placed over each other and/or within recesses of an adjustment layer and held together by the overlying trim material **22**. In other embodiments, such as schematically illustrated in FIG. 6, the one or more layers **30-34** can have a mechanical fastening component schematically illustrated at **50** in FIG. 6. In at least one embodiment, the mechanical fastening component **50** can comprise a male protrusion **52** that is receivable within a female recess **54** in an adjacent layer.

[0039] In at least other embodiments, the mechanical fastening component **50** could comprise an adhesive layer. In keeping with the environmentally friendly considerations of the vehicle seat assembly **10**, any adhesive layer that is used should be compatible with one or more of the adjacent layers for ease of recycling. For example, a polyester-based adhesive can be used to adhere polyester trim **22** to a non-woven polyester comfort layer **34** thereby maintaining common polymer content in that layer. Similarly if attachment clips are used in the polyurethane layer, they could be molded out of thermoplastic polyurethane (TPU) to again preserve commonality of polymer content in the layer. When separated, the TPU clips could remain in the support polyurethane layer.

[0040] As discussed above, the vehicle seat assembly **10** of the present invention is readily recyclable. In this regard, the layers **30-34** can be easily separated from each other and from the trim material **22** in a relatively easy and straightforward fashion. For instance, the layers **30-34** can be separately recycled without any difficulty and recycled in separate streams.

[0041] Referring to FIG. 5, an alternative embodiment of the seat assembly **10** is illustrated. In this embodiment, seat frame **14** illustrated in FIGS. 1-4 is omitted. Such a configuration is typically more practical in second and third row seats.

[0042] While embodiments to the invention has been illustrated and described, it is not intended that these embodiments illustrate and describe all possible forms of the invention. Moreover, the words used in the specification are words of description rather than limitation, and it is understood that various changes may be made without departing from the spirit and scope of the invention.

What is claimed is:

1. A vehicle seat assembly comprising:

a cushion composite comprising a molded expanded polyolefin structural layer and a foam cushion layer, the foam cushion layer having an upper surface, bottom surface, and a hysteresis of 18 to 30 KPa, the foam cushion layer being substantially adjacent the structural layer and in

substantially uninterrupted contact with the structural layer across substantially the entire bottom surface; and a trim material secured over the cushion composite, wherein the cushion layer, the comfort layer and the trim material are not secured to each other such that they are separable from each other.

2. The vehicle seat assembly of claim **1** wherein the foam cushion layer is made of polyurethane and has a rigidity that is less than the rigidity of the structural layer.

3. The vehicle seat assembly of claim **1** further comprising a frame, wherein the structural layer is disposed between the frame and the cushion layer.

4. The vehicle seat assembly of claim **3** wherein the expanded polyolefin comprises expanded polypropylene and the cushion layer comprises soy-based polyurethane.

5. The vehicle seat assembly of claim **1** wherein at least one of the cushion layer and the structural layer includes molded polymeric attachment clips.

6. The vehicle seat assembly of claim **1** further comprising a comfort pad disposed between the foam cushion layer and the trim material.

7. The vehicle seat assembly of claim **6** wherein the structural layer has an average thickness of 5 to 100 mm, the cushion layer has an average thickness of 20 to 100 mm, and the comfort pad has an average thickness of 2 to 30 mm.

8. The vehicle seat assembly of claim **7** wherein the comfort pad is made of non-woven compressed fibrous material.

9. The vehicle seat assembly of claim **8** wherein the trim material is made of polymeric material.

10. The vehicle seat assembly of claim **4** wherein the structural layer has a density of 1.75 to 7.0 pcf.

11. The vehicle seat assembly of claim **10** wherein the structural layer has a hardness of 150 to 250 N, and a compression strength of 20 to 100 psi.

12. The vehicle seat assembly of claim **1** wherein the structural layer has a density of 1.75 to 7.0 pcf, a hardness of 150 to 250 N, and a compression strength of 20 to 100 psi and wherein the cushion layer has a density of 1.5 to 4.5 pcf.

13. A vehicle foam component assembly comprising:
a cushion composite comprising a molded expanded polyolefin structural layer and a foam cushion layer having a bottom surface and a hysteresis of 18 to 30 KPa, the foam cushion layer being substantially adjacent to the structural layer and in substantially uninterrupted contact with the structural layer across the bottom surface, wherein the cushion layer has a density of 1.5 to 4.5 pcf, and wherein the density of the cushion layer is less than a density of the structural layer; and

a trim material secured over the cushion composite.

14. The vehicle foam component assembly of claim **13** further comprising a comfort pad disposed between the structural layer and the trim material.

15. The vehicle foam component assembly of claim **13** wherein the structural layer has a density of 1.75 to 7.0 pcf.

16. The vehicle foam component assembly of claim **13** wherein the structural layer has a hardness of 150 to 250 N.

17. The vehicle foam component assembly of claim **15** wherein the structural layer has a compressive strength of 20 to 100 psi.

18. A vehicle seat assembly comprising:

a cushion composite comprising a structural layer and a cushion layer adjacent to the structural layer;

first securing means for holding the structural layer and cushion layer together; and

a trim layer secured over the cushion composite by a second securing means,

wherein the first and second securing means are non-permanent securing means which enable the structural layer, cushion layer and trim layer to be disassembled and separated for recycling.

19. The vehicle seat assembly of claim **18** wherein the structural layer has an average thickness of 5 to 100 mm and the cushion layer has an average thickness of 20 to 100 mm.

20. The vehicle seat assembly of claim **19** wherein the structural layer has a density of 1.75 to 7.0 pcf (28.04 to 112.14 kg/m³) and a hardness of 150 to 250, and the cushion layer has a density of 1.5 to 4.5 pcf (24.03 to 72.08 kg/m³), and a hysteresis of 18 to 30 KPa.

* * * * *